

<b>Characteristics</b>	<b>Luxury RigidCore Plank Floating Floor with IXPE Underlayment and Superior click system</b>
<b>Description</b>	Plank Size 7" Wide x 48" Long (Registered & Embossed) Plank Size 8.86" Wide x 48" Long (Registered & Embossed)
<b>Size / Thickness</b>	6.5mm Total Thickness (5.0mm Core + 1.5mm IXPE + 0.5mm Wearlayer)
<b>Installation</b>	Click System - Floating
<b>Warranty</b>	Lifetime Residential Wear Warranty Lifetime Structural Warranty
<b>Heat Resistance &amp; Color Stability</b>	ISO 23999 - Final Curl Avg 0.37mm ASTM F1514 - After 7 days of accelerated heat in the chamber, No Change occurred.
<b>Color Change - Light Stability</b>	ASTM F1515 - 100-300 Hours Direct accelerated light - Resulting in nearly No Change
<b>Impact Resistance</b>	ASTM F1914 - 0.002" after 60min recovery time - Surface Integrity - No puncture through wear layer
<b>Static Load Limit</b>	ASTM F970 - Results 0.002" - Exceeding Classification (34) requirements
<b>Castor Chair Resistance</b>	Classification (34) No visible damage effects from furniture leg testing.
<b>Approximate IIC Rating on 6" Thick Concrete Slab Floor (150 lbs/cu ft)</b>	IIC: 52 - (IIC: 64 with drop ceiling) STC: 49 - (STC: 61 with drop ceiling)
<b>Resistance to Chemical</b>	ASTM F925 - No change occurred to product after exposure
<b>Fire Rating</b>	ASTM E648 - Results "Exceeds Class 1 rating as specified in NFPA Life Safety Code 101
<b>Peel Strength ISO 24345:2006</b>	Mean Value: MD 110 N/50mm; AMD 105 N/50mm
<b>Fungi Resistance ASTM G21-15</b>	Unlike Cork, this product shows zero "None" results for observed growth.
<b>FloorScore®</b>	SCS-FS-04026   2016.06.01 - 2017.05.31
<b>Packaging</b>	
<b>Content of Box</b>	(7" x 48" - 18.91Sq.Ft./ Box ) & (8.86" x 48" - 17.73Sq.Ft. / Box)
<b>Content of Pallet</b>	(55 cartons - 2,211.02lbs - 7" Profile) & (56 cartons - 2,113.23lbs - 8.86" Profile)